

HardiePlank® Lap Siding

Submittal Form

01

Submitted to:

Project Name:

Submitted by:

Date:

☐ HZ5® Product Zone

☐ HZ10® Product Zone

Product Width: ☐ 5-1/4in ☐ 6-1/4in ☐ 7-1/4in ☐ 8in ☐ 8-1/4in ☐ 9-1/4in ☐ 12in

Product Finish: ☐ Primed ☐ ColorPlus® Technology

Product Texture: ☐ Smooth ☐ Select Cedarmill® ☐ Colonial Roughsawn®
☐ Colonial Smooth® ☐ Rustic Cedar

HardiePlank® Lap Siding

Specification Sheet

01

DIVISION: 07 00 00 THERMAL AND MOISTURE PROTECTION

SECTION: 07 46 46 FIBRE CEMENT SIDING

HARDIEPLANK® LAP SIDING

Manufacturer

James Hardie Building Products, Inc

The products are manufactured at the following locations, with quality control inspections by ICC-ES:

- Cleburne, Texas
- Plant City, Florida
- Reno, Nevada
- Waxahachie, Texas
- Peru, Illinois
- Pulaski, Virginia
- Tacoma, Washington
- Fontana, California

Compliance with the following codes

- 2012, 2009 and 2006 International Building Code® (IBC)
- 2012, 2009 and 2006 International Residential Code® (IRC)

Features

- Noncombustible
- Dimensionally Stable
- Resists damage from pests
- Weather Resistant-Engineered for Climate®
- Impact resistant
- Sustainable

Use

James Hardie fiber-cement lap siding is used as exterior wall covering. The product complies with IBC Section 1404.10 and IRC Section R703.10. The product may be used on exterior walls of buildings of Type I, II, III and IV construction (IBC)

Description

HardiePlank lap siding is a single-faced, cellulose fiber-reinforced cement (fiber-cement) product. HardiePlank lap siding complies with ASTM C1186, as Grade II, Type A; has a flame-spread index of 0 and a smoke-developed index of 5 when tested in accordance with ASTM E84; and is classified as noncombustible when tested in accordance with ASTM E136.

Available Sizes

Product	Width (in)	Length	Thickness (in)
HardiePlank lap siding*	5-1/4, 6-1/4, 7-1/4, 8, 8-1/4, 9-1/4, 12	12 feet	5/16

* HZ5: 9-1/4, 12 only available primed HZ10: 5-1/4, 9-1/4, 12 only available primed.

Texture & Finish

HardiePlank lap siding comes in a variety of textures and finishes. The product is available in smooth or wood grain texture. Additional textures are available on a regional basis. Finish options are primed for field paint, or factory finished with ColorPlus® Technology. Color availability varies by region.

Engineered for Climate®

HardiePlank lap siding is engineered for performance to specific weather conditions by climate zones as identified by the following map.



Performance Properties

General Property		Test Method	Unit or Characteristic	Requirement	Result
PHYSICAL ATTRIBUTES	Dimensional Tolerances	ASTM C1185	Length	$\pm 0.5\%$ or $\pm 1/4$ in	Pass
			Width	$\pm 0.5\%$ or $\pm 1/4$ in	
			Thickness	± 0.04 in	
			Squareness	$<1/32$ in/ft of length	
			Edge Straightness	$<1/32$ in/ft of length	
	Density, lb/ft ³	ASTM C1185		As reported	83
	Water Absorption, % by mass	ASTM C1185		As reported	36
THERMAL	Water Tightness	ASTM C1185	Physical Observations	No drop formation	Pass
	Flexural Strength	ASTM C1185	Wet conditioned, psi	>1015 psi	Pass
			Equilibrium conditioned, psi	>1450 psi	
	Thermal Conductivity	ASTM C177	(BTU/(hr·ft ² ·F))/inch	As reported	2.07
DURABILITY	Actual Thermal Conductivity		(K _{eff})		6.62
	Thermal Resistance		R=1/ K _{eff}		0.48
	Actual Thermal Resistance		(R)		0.15
	Warm Water Resistance	ASTM C1185	Physical Observations	No visible cracks or structural alteration	Pass
FIRE CHARACTERISTICS	Heat/Rain Resistance	ASTM C1185	Physical Observations	No visible cracks or structural alteration	Pass
	Freeze/Thaw Resistance	ASTM C1185	Physical Observations	No visible cracks or structural alteration	Pass
			Mass Loss, %	$\leq 3.0\%$	
	UV Accelerated Weathering Test	ASTM G23	Freeze/Thaw, % strength retention	$\geq 80\%$	Pass
			Physical Observations	No cracking, checking, or crazing	
FIRE CHARACTERISTICS	Surface Burning Characteristics	ASTM E84	Flame Spread Index (FSI)		0
			Smoke Developed Index (SDI)		≤ 5
			Fuel Contributed		0
			NFPA Class		A
	Noncombustibility	ASTM E136	Uniform Building Code Class	As reported	1
			International Building Code® class		A
FIRE CHARACTERISTICS	Noncombustibility	ASTM E136	Noncombustible	Pass/fail	Pass
	Fire Resistance Rated Construction	ASTM E119	Fire Resistance Rating	1-hour	Note 1

Note 1: listed on Warnock Hersey and ESR 2290

Installation

Install HardiePlank lap siding in accordance with:

- HardiePlank lap siding installation instructions
- ICC-ES ESR 2290
- Requirements of authorities having jurisdiction

Warranty

HardiePlank lap siding: 30-year, Non-Prorated, Limited Warranty
ColorPlus Technology: 15-year Limited Finish Warranty

Sustainable Design Contribution

- Regionally sourced content- varies by project location
- Avoidance of certain chemicals or Red List Compliance

Detailed product information for LEED projects, or other state or regional sustainability programs is available through James Hardie Technical Services.

Storage and Handling

Store flat and keep dry and covered prior to installation.

Technical Services

Contact James Hardie Technical Services online at JamesHardie.com, or by phone at (800)426-4051



Additional Installation Information, Warranties, and Warning are available at JamesHardie.com

1 866 442 7343 | www.jameshardie.com

IMPORTANT: Failure to install and finish this product in accordance with applicable building codes and James Hardie written application instructions may affect system performance, violate local building codes, void the product-only warranty and lead to personal injury.

DESIGN ADVICE: Any information or assistance provided by James Hardie in relation to specific projects must be approved by the relevant specialists engaged for the project eg. builder, architect or engineer. James Hardie will not be responsible in connection with any such information or assistance.

© 2018 James Hardie Building Products Inc. All rights reserved. TM, SM, and ® denote trademarks or registered trademarks of James Hardie Technology Limited. The International Building Code and International Residential Code trademarks are registered trademarks of International Code Council, Inc. TB1001 07/14